



CZECH TECHNICAL UNIVERSITY IN PRAGUE  
FACULTY OF CIVIL ENGINEERING – TEST LABORATORY  
Test laboratory No. 1048 accredited by ČIA according to  
ČSN EN ISO/IEC 17025:2018  
Thákurova 7, 166 29 Praha 6



L 1048

**SPECIAL LABORATORY OL 124**

Tel.: +420224354806

E-mail: [jiranek@fsv.cvut.cz](mailto:jiranek@fsv.cvut.cz)

Number of pages : 2

Page Number : 1

## TECHNICAL INFORMATION

### Radon resistance and radon transmittance of the waterproofing material BLOWERPROOF LIQUID

**Client:**

CEO HEVADEX Group  
Spinnerslaan 6  
9160 Lokeren  
Belgium

**Date of issue: 3.9.2019**

**Prepared by:**



.....  
**prof. Ing. Martin Jiránek, CSc.**  
head of OL 124 laboratory

Radon diffusion coefficient **D** of the Blowerproof Liquid waterproofing material was determined by the accredited test laboratory No.1048 of the Czech Technical University in Prague, Faculty of Civil Engineering, special laboratory OL124. Based on the test report No. 124015/2017 issued on 5.4.2017, the radon diffusion coefficient **D** = (3,3±0,3).10<sup>-12</sup> m<sup>2</sup>/s.

Radon diffusion coefficient **D** stated in the test report mentioned above is a material constant that shows the ability of radon to diffuse in the material.

The ability of a waterproofing product to form an efficient barrier against radon diffusion is expressed by the **radon resistance** **R<sub>Rn</sub>** or the **radon transmittance** **T<sub>Rn</sub>** that are defined according to the following equations.

$$R_{Rn} = \frac{\sinh(d/l)}{\lambda \cdot l} \quad [\text{s/m}]$$

$$T_{Rn} = \frac{1}{R_{Rn}} = \frac{\lambda \cdot l}{\sinh(d/l)} \quad [\text{m/s}]$$

where **d** is the dry thickness of the product [m], **λ** is the radon decay constant [2,1.10<sup>-6</sup> s<sup>-1</sup>] and **l** is the radon diffusion length in the material [m] calculated as follows:  $l = \sqrt{D/\lambda}$ . Radon resistance and radon transmittance values of the tested product depending on its dry thickness are shown in the following table. Greater value of the radon resistance means better barrier properties.

#### Radon resistance and radon transmittance values for specified thicknesses

<b>d [mm]</b>	<b>D [m<sup>2</sup>/s]</b>	<b>l [m]</b>	<b>R<sub>Rn</sub> [s/m]</b>	<b>T<sub>Rn</sub> [m/s]</b>
0,5	3,3.10 <sup>-12</sup>	1,25.10 <sup>-3</sup>	156.10 <sup>6</sup>	6,4.10 <sup>-9</sup>
0,6			189.10 <sup>6</sup>	5,3.10 <sup>-9</sup>
0,7			223.10 <sup>6</sup>	4,5.10 <sup>-9</sup>
0,8			259.10 <sup>6</sup>	3,9.10 <sup>-9</sup>
0,9			297.10 <sup>6</sup>	3,4.10 <sup>-9</sup>
1,0			336.10 <sup>6</sup>	3,0.10 <sup>-9</sup>

Applicability of the tested material for a radon-proof product can be in a particular case considered in accordance with national building codes or standards.

#### References

Jiránek M., Kačmaříková V.: Radon diffusion coefficients and radon resistances of waterproofing materials available on the building market. Journal of Environmental Radioactivity (2019), doi.org./10.1016/j.jenvrad.2019.106019

Jiránek, M. New, efficient and generally applicable design of radon-proof insulations – a proposal for a uniform approach. Radiation Protection Dosimetry (2017), Vol. 177 (1-2), pp. 121-124, doi. 10.1093/rpd/ncx139

Jiránek, M. and Svoboda, Z. A new approach to the assessment of radon barrier properties of waterproofing materials. Radiation Protection Dosimetry (2017), Vol. 177 (1-2), pp. 116-120, doi. 10.1093/rpd/ncx140