



Technical Data Sheet

MENOS Natural Undercoat No. 626

Suitable for	A primer for interior wooden surfaces. Also suitable for glass fibre wallpaper.
Technical qualities	Flexible, matt.
Full declaration	Chalk, titan dioxide, isoaliphates, linseed-stand-oil natural resin ester, mica, talcum, orange oil, silicic acid, bentonite, citron oil, dehydrated amino sugar, ethanol and drying agents free of lead (Ca, Co, Zr).
Color	White.
Dilution	With SVALOS Thinner No. 222.
Application method	Apply sparingly using a brush, roller (undiluted) or spraying device (maximum 10 % dilution) at temperatures above 15 ⁰ C and low humidity.
Coverage	Determine with a test application! One undiluted liter is sufficient for 10-15 m ² per coat, i.e. 80 ml/m ² . Could be considerably less depending on the absorbency and the surface condition of the wood. Each dried coating may not exceed 50µm.
Specific gravity	Approximately 1.45 g/ml.
Drying time	At 23 °C and 50 % relative humidity, dry to the touch after approximately 3 hours. Sanding and subsequent coating may be done after 24 hours. The paint is fully hardened after 6 - 7 days. A coat applied too thickly, low temperatures or high humidity can cause drying delays.
Cleaning up	Clean equipment immediately after use With SVALOS Thinner No.
Safety advice	Provide enough ventilation after application. Always be sure to store and then dispose cleaning cloths, polishing pads, sponges, etc. that are still wet or even slightly moist with MENOS Natural Undercoat No. 626 in an airtight metal container or in water, as there is a danger of spontaneous combustion caused by the plant oil content. The product itself will not combust spontaneously. Contains limonene and cobalt (2+) salts. Can cause allergic reactions. S2 Keep out of reach of children. S62 If swallowed, do not induce vomiting. Seek medical assistance immediately, and show label or data sheet information.
Disposal	According to locally regulated laws.
Container sizes	0.05 lt; 0.375lt; 0.75lt; 2.5lt; 5lt.
Storage	Cool and dry. Close opened product tightly and transfer unused portions into a smaller container for storage.

Preparation

Surface must be dry (wood moisture content under 15%), solid, clean, and free of grease, resin and dust.
If wooden surfaces have small damages or cracks, putty and sand either partially or the entire area, if necessary.

Application

Stir thoroughly before use.
Apply a sparing base coat of MENOS Natural Undercoat No. 626 with a brush, roller or spraying device at temperatures above 15⁰C.
Subsequent treatment with CANTO Paint No. 625 or VINDO Natural Gloss Paint No. 629 (high gloss).

Renovation

Non-intact old coatings must be completely removed. Follow preparation and application instructions for untreated wood as above. If old coating is intact sand intact old coatings well and test compatibility by painting with 5 -10 % diluted CANTO Paint No. 625 or VINDO Natural Gloss Paint No. 629 (high gloss).

Important tips

MENOS Natural Undercoat No. 626 should be applied sparingly. Spray applications must also be allowed to dry thoroughly. Too thickly applied coatings can impair drying properties and can cause cracking of subsequent paint coats.

MENOS Natural Undercoat No. 626 contains few solvents; this may cause a skin to build up. Please, remove before stirring. Transfer unused portions into smaller containers for storage.

No liability is assumed for possible impaired adhesion as well as the development of odors resulting when MENOS No. 626 is painted over by products of other manufacturers. Do not paint over silicone.

Applying MENOS Natural Undercoat No. 626 mixed with 5 % by volume of quartz sand to plaster, will prevent impurities (e.g. nicotine or dried water spots) from surfacing. Subsequent coating with DUBRON Natural Dispersion Paints No. 400 or 412.

These directions are the result of long years of research and practical testing. They are backed by our most current expert information. New findings may invalidate this information. This data sheet is meant to serve as information and instruction.

No legal liability should be interpreted from it. In case of doubt, please contact the retailer, wholesaler, or manufacturer.

March 2011 Rev. 2.1