



# BLOWERPROOF<sup>®</sup> LIQUID

Hi-technology polymer emulsion that dries to form  
a permanent flexible airtight membrane.  
Apply with an airless paint spray machine.



## DESCRIPTION

BLOWERPROOF LIQUID is a voc free polymer based liquid, that is applied with an airless paint spray device and dries to an airtight flexible coating with a good adhesion on different surfaces such as concrete, brick, wood, ...

### Field of use:

- » Floor/wall connections
- » Wall/ceiling connections
- » Entire walls
- » Wall/wall connections
- » Vertical and horizontal joints

## APPLICATION

### PRIOR TO STARTING THE APPLICATION

- » Remove salt efflorescence, dust, loose parts and standing water from the surface.
- » Apply on a closed surface; if necessary, fill holes and joints with a fast setting cement based product or polyurethane foam; Apply BLOWERPROOF LIQUID BRUSH on holes and joints < 5mm.
- » Do not apply BLOWERPROOF LIQUID at T < 5°C (also substrate temperature)
- » Application on humid surfaces is allowed, but remove standing water.

### APPLICATION

- » BLOWERPROOF LIQUID is ready-to-use; mix with hand mixer before application. Do not dilute with water or solvents.
- » Apply with an airless paint spray device. - Kindly contact us for more information: [info@hevadex.be](mailto:info@hevadex.be)
- » Cleaning airless device: with water.
- » Apply BLOWERPROOF LIQUID in two layers, at a total consumption of 0,5 - 1 kg/m<sup>2</sup>.
- » Complete drying is requested prior to applying another product on BLOWERPROOF LIQUID (such as plaster). Drying time may vary and depends on local conditions and condition of the substrate.  
Indicative: 24 - 48 hours.



# BLOWERPROOF<sup>®</sup> LIQUID

**CHARACTERISTICS**

**TESTREPORTS AND CERTIFICATIONS**

This table contains average values from reports and certifications from independent building testing institutes. Values obtained after ageing of the samples are marked with « v ».

TEST INSTITUTE	TEST	NORM	VALUE
bbri.be	Damp diffusion resistance factor	EN ISO 12572 (2001)	$\mu = 76584$
bbri.be	Adhesion on red brick Porotherm (dry)	ISO4624 (2002)	1,5 N/mm <sup>2</sup> (v)
bbri.be	Adhesion on red brick Porotherm (moist)	ISO4624 (2002)	1,4 N/mm <sup>2</sup> (v)
bbri.be	Adhesion on concrete brick (dry)	ISO4624 (2002)	1,9 N /mm <sup>2</sup> (v)
bbri.be	Adhesion on concrete brick (moist)	ISO4624 (2002)	1,6 N /mm <sup>2</sup> (v)
bbri.be	Adhesion on Ytong block (dry)	ISO4624 (2002)	0,8 N /mm <sup>2</sup> (v); 100% failure in the substrate
bbri.be	Adhesion on Ytong block (moist)	ISO4624 (2002)	0,7 N /mm <sup>2</sup> (v) >70% failure in the substrate
bbri.be	Adhesion on gypsum block (Isolava)	ISO4624 (2006)	1,6 N /mm <sup>2</sup>
bbri.be	Adhesion on OSB wood	ISO4624 (2002)	0,6 N /mm <sup>2</sup> (v) >70% failure in the substrate
bbri.be	Adhesion on multiplex wood	ISO4624 (2002)	0,6 N /mm <sup>2</sup> (v) >50% failure in the substrate
bbri.be	Adhesion on steel	ISO4624 (2002)	2,7 N /mm <sup>2</sup>
bbri.be	Adhesion on EPDM (« Tridex »)	ISO4624 (2002)	1,3 N /mm <sup>2</sup> (v)
bbri.be	Adhesion on roofing	ISO4624 (2002)	0,7 N /mm <sup>2</sup> ; 100% failure in the substrate
bbri.be	Adhesion of sprayed plaster (knauf MP75) on Blowerproof Liquid	ISO4624 (2002)	0,4 N /mm <sup>2</sup> (v); >40% failure in the plaster
bbri.be	Adhesion of thin plaster (ALLTEC) on Blowerproof Liquid	ISO4624 (2006)	0,8 N /mm <sup>2</sup> (v);
bbri.be	Elongation	NBN EN 12311-1 (1999)	230% (V); 20 N/50mm <sup>2</sup> tensile strength
UNIVERSITY OF GHENT (BELGIUM)	Airtightness floor/wall after ageing	NBN EN 12114:2000 Eurocode 7	0,07 M <sup>3</sup> /H.M (50BAR) (V)
warringtonfiregent	Flame propagation	EN ISO 11925-2	<150 mm
warringtonfiregent	Fire reaction	EN ISO 11925-2	NO
VIT	VOC, TVOC, carcinogenics, ammonia, formaldehyde	EN ISO 16000-9/6 EN 717-1 EN ISO 16000-28	
Mecadi	Methane permeability	ISO 15105	62 – 75 cm <sup>3</sup> (STP)·mm·m <sup>-2</sup> ·day <sup>-1</sup> ·atm <sup>-1</sup>



# BLOWERPROOF<sup>®</sup> LIQUID

### ADDITIONAL TESTREPORTS

BCB	Airtightness of floor/wall connection
BCB	Airtightness of entire walls, with anchored insulation
Airtightness reports (blowerdoor) of realized projects	

### OTHER CHARACTERISTICS

- » Average consumption: 0,5 - 1 kg/m<sup>2</sup> (indicative, depending on substrate)
- » Density: +/- 1,2 kg / litre
- » Available colours:
  - blue (drying to black airtight coating)
  - white (drying to white airtight coating)
- » Indicative drying time: 0,5 to 24 hours (depending on substrate temperature, air humidity, applied layer thickness and ventilation).
- » Storage: 5 – 20 °C; stored dry, out of direct sunlight; conservation: 12 months from date of production, original unopened packaging.

### PACKAGING

10kg pails – pallet : 44 x 10 kg

### SAFETY

Consult the safety data sheet prior to application. Always work in well-ventilated areas. Avoid skin contact when product is in wet condition. Requested to wear eye protection, mouth mask, gloves and safety wear during application.

Distributed by:



tel: 01793 847 444  
email: [info@ecomerchant.co.uk](mailto:info@ecomerchant.co.uk)  
web: [www.ecomerchant.co.uk](http://www.ecomerchant.co.uk)

DATE OF THIS EDITION: 04/11/2016

Our general conditions of sale apply. This document does not have a contractual value. This technical data sheet replaces and annuls the previous edition. The information given in this sheet has the purpose to inform and advice you. At every moment, this sheet can be adapted because of technical evolution. All information is given in good faith and without any warranty. The application, use and processing of these products are beyond our control and therefore the entire responsibility of the user/client/applicator. The user of the product must test the product's suitability and apply for the intended purpose. Established liability if any for any reason is always limited to the value of the goods supplied by HEVADEX bvba. The products and systems are manufactured under total quality management. HEVADEX bvba reserves the right to change the properties of its products. Users must always refer to the most recent issue of the local Product Data Sheet, copies of which will be supplied on request.